




Tuch Lymtech

pure¹¹-Nr.: 06219, Hersteller: ESSENTRA



Zusammenfassung

- Neue pure¹¹-Artikelnummer (ab 01.07.2023): 1106219
- Material: Polyester/Zellulose
- Gewicht: 68 g/m²
- Tränkung: Keine
- Vliesstoff (55% Zellulose/45% Polyester)
- Hydroverfestigt (nonwoven)
- Fusselarm
- Gammasterilisiert (inkl. Sterilisationszertifikat)
- Lieferform: gelegt

Empfohlene Reinraumklassen

ISO

3

4

5

6

7

8

9

GMP



A/B



C

D



Produktvarianten

pure¹¹-Nr.: 062193030

Farbe: Weiß / Maße: 31 x 31 cm (12 x 12") / Herst.-Nr.: C30GR / VE: 150 Stück

Quelle: <https://www.pure11.de/tuch-lymtech>

pure¹¹ GmbH

Bavariafilmpfad 7 | D-82031 Grünwald

Geschäftsführer: Gitte Hansen, Julian Kropp

AG München HRB 171307

T +49 89 5589434 0

F +49 89 5589434 77

www.pure11.de

info@pure11.de



2255 Westover Road
 Chicopee, Massachusetts • 01022
 Tel 413.592.4111 • Fax 413.592.4112
 800.628.8606
<http://www.lymtech.com>

C30GR

Hydroentangled blend of 55% cellulose / 45% polyester. Gamma irradiated to a minimum dose of 25 kGy and a maximum dose of 40 kGy.

Property	Typical Value	Test Method
Basis Weight		
(oz/yd ²)	2.0	
(g/m ²)	68	
Thickness		
(mils)	12	
(mm)	0.305	
Sorptive Capacity		
Intrinsic (mL/g)	4.19	IEST-RP-CC004.3
Extrinsic (mL/m ²)	291	IEST-RP-CC004.3
Extractables (mg/g)		
DI Water, DIW	0.110	IEST-RP-CC004.3
Isopropyl Alcohol, IPA	0.171	IEST-RP-CC004.3
Ions (ppm)		
Sodium	2.4	IEST-RP-CC004.3
Chloride	24	IEST-RP-CC004.3
Particles (million/m²)		
0.5 - 5.0 µm	46.5	IEST-RP-CC004.3
5.0 - 100 µm	0.51	IEST-RP-CC004.3
Fibers (fibers/m²)		
>100 µm	43,900	IEST-RP-CC004.3

Notes:

- 1) Data shown are typical values and should not be used as product specifications.
- 2) Valid product comparisons may only be obtained through side-by side testing in the same test facility, under similar conditions. Current and/or comparison data may be available. Please contact a LymTech representative for details.
- 3) LymTech makes general recommendations on which wipers are suitable for different cleanroom classifications. However, specific applications may affect that recommendation. The final decision should be made by the end user for their particular application.