

Reinraum-Klebeband Vinyl Surface-Protection #1310-0,75

pure[11]-Nr.: 1130016, Marke: UltraTape

Eigenschaften

- Marke: UltraTape
- Breite in cm: 1,9 cm
- Klebestärke: leicht
- Klebstoff: Acryl
- PVC: 100 %
- Rückstandsfrei ablösbar

Empfohlene Reinraumklassen

ISO 4 | 5 | 6 | 7 | 8 | 9

GMP C | D

we care

pure[11] GmbH |
Bavariafilmplatz 7 | D-82031 Grünwald
T +49 89 5589434 0
F +49 89 5589434 77
www.pure11.de
info@pure11.de

Material

-

Verpackung

- 8STK

Produktvarianten

pure¹¹-Nr.: 1130016TP0_75I, Reinraum-Klebeband Vinyl Surface-Protection #1310-0,75

Farbe: Transparent; Breite: 0,75" / VE: 8STK

pure¹¹ GmbH |
Bavariafilmplatz 7 | D-82031 Grünwald
T +49 89 5589434 0
F +49 89 5589434 77
www.pure11.de
info@pure11.de

UltraTape
Adhesive Tape & Labels for Critical Environments

PRODUCT DATASHEET

UT1310 Vinyl Surface Protection Low Adhesion Cleanroom Tape

DESCRIPTION

UltraTape 1310 / 0310 cleanroom tape is used for protection of surface finishes from dirt, scratches and tool marks during handling, transport and storage. Useful on smooth / medium to high gloss finished glass, painted metal or aluminum.

- Protect surfaces during processing, storage or shipping
- Low adhesion, easy clean removal without residue
- Available in almost any width
- Cleanroom certified

PROPERTIES

Backing	PVC
Adhesive	Acrylic
Total Thickness	3.0 mils / 50µm
Elongation	200%
Adhesion to Stainless Steel	5.0 oz/in (55 cN/cm)
Release Liner	N/A
Operating Temperature	60°F to 122°F (15°C to 50°C)
Breaking Strength	14.0 lbs./in (2.45 daN/cm)
Length	55 yards
Colors	Transparent Blue

To achieve ultimate adhesion, the bonding surface should be clean, dry, and free of dirt and oils. The strength of the adhesive bond is dependent on the amount of surface area directly in contact with the adhesive. Firm pressure is recommended to achieve good adhesive to surface contact.

UltraTape recommends that each user conduct their own test to determine the product's suitability for the intended application and shall assume all risks and liabilities in connection therewith. Materials should be stored at 70°F (21C°) with 50% relative humidity.

9770 SW Wilsonville Road, Suite 400
Wilsonville, OR 97070
www.cleanroomtape.com

503.427.2880
503.482.5616

© UltraTape 2022 | Rev. 05/2022

ISO 9001:2015

UL LISTED

A division of DELPHON