

UltraTape



Reinraum-Klebeband Polyimide High-Temp #2158-1

pure¹¹-Nr.: 1130021, Marke: UltraTape

Eigenschaften

- Marke: UltraTape
- Breite in cm: 2,54 cm
- Chemikalienbeständigkeit
- Klebestärke: mittel
- Klebstoff: Acryl
- Rückstandsfrei ablösbar
- Temperaturbeständig

Empfohlene Reinraumklassen

ISO 4|5|6|7|8|9

GMP C|D

pure¹¹ GmbH

Bavariafilmplatz 7 | D-82031 Grünwald

Geschäftsführung: Julian Kropp, Linda Vereycken, Lars Engeler

AG München HRB 171307

T +49 89 5589434 0

F +49 89 5589434 77

www.pure11.de

info@pure11.de

Material

-

Verpackung

- 6STK

Produktvarianten

pure¹¹-Nr.: 1130021BZ1I, Reinraum-Klebeband Polyimide High-Temp #2158-1

Farbe: Bronze; Breite: 1" / VE: 6STK

pure¹¹ GmbH

Bavariafilmplatz 7 | D-82031 Grünwald

Geschäftsführung: Julian Kropp, Linda Vereycken, Lars Engeler

AG München HRB 171307

T +49 89 5589434 0

F +49 89 5589434 77

www.pure11.de

info@pure11.de

UT2158 Polyimide Cleanroom Tape with Acrylic Adhesive

DESCRIPTION

UltraTape 2158 / 0158 is a high temperature polyimide cleanroom tape with acrylic adhesive. It has excellent thermal resistance and electrical insulating properties.

- Removes with no adhesive residue
- Resistant to tearing and punctures
- Bonds to low energy surfaces
- Cleanroom certified

PROPERTIES

Backing	Polyimide
Adhesive	Acrylic
Backing Thickness	1.0 mil (0.0254 mm)
Adhesive Thickness	1.5 mils (0.0381 mm)
Adhesion to Stainless	25 oz/in (6.95 N/25.4 mm)
Operating Temperature	-20°F to 311°F (-29°C to 155°C)
Dielectric Strength	6500 Volts
Tensile Strength	32 lbs./in (142.34 N/25.4mm)
Length	36 yards
Colors	Bronze (BZ)

To achieve ultimate adhesion, the bonding surface should be clean, dry, and free of dirt and oils. The strength of the adhesive bond is dependent on the amount of surface area directly in contact with the adhesive. Firm pressure is recommended to achieve good adhesive to surface contact.

UltraTape recommends that each user conduct their own test to determine the product's suitability for the intended application and shall assume all risks and liabilities in connection therewith. Materials should be stored at 70°F (21°C) with 50% relative humidity.