Empfohlene Reinraumklassen

ISO 5 | 6 | 7 | 8 | 9

GMP C | D

Tuch Sontara MicroPure SV

pure[11]-Nr.: 1106038, Marke: Sontara

Eigenschaften

- Marke: Sontara
- Flächengewicht in g/m²: 51 g/m²
- Struktur: Vliesstoff
- Material: Polyester/Zellulose
- Lieferform in Verpackung: gelegt
- Verpackungsform: Beutel
- Anzahl in kleinster Unterverpackung: 500
- Besonders reißfest
- Chemikalienbeständigkeit
- Gebrauch: Einweg
- Flächengewicht in g/m²: 51 g/m²

pure[11] GmbH |
Bavariafilmplatz 7 | D-82031 Grünwald
T +49 89 5589434 0
F +49 89 5589434 77
www.pure11.de
info@pure11.de

we care

Material

- Polyester/Zellulose

Verpackung

- 10000STK

Produktvarianten

pure[11]-Nr.: 11060382323WH, Tuch Sontara MicroPure SV

Größe: 23 x 23 cm (9 x 9"); Farbe: Weiß / VE: 10000STK

pure[11]-Nr.: 11060383131WH, Tuch Sontara MicroPure SV

Größe: 31 x 31 cm (12 x 12"); Farbe: Weiß / VE: 5000STK

Sontara®

TECHNICAL DATA SHEET

MICROPURE SV
50.4% Woodpulp – 49.6% PET
Flat
White

TYPICAL MATERIAL PROPERTIES

Test	Orientation	Units	Targets	Methods
Basis Weight		g/m^2	51	WSP 130.1
Thickness		mm	0.38	WSP 120.6
Absorption Capacity		%	663	WSP 10.1
Extrinsic absorption Capacity		ml/m^2	340	WSP 10.2
Grab Tensile Strength	MD	N/4in	106	ASTM D5034
Grab Tensile Strength	CD	N/4in	53	ASTM D5034
Particles BAS		MM/m^2	35	IEST-RP-CC004.3
Particle Po		MM/m^2	66.2	IEST-RP-CC004.3
Extractables DI Water		%	0.061	IEST-RP-CC004.3
Extractables IPA		%	0.02	IEST-RP-CC004.3

WSP = Worldwide Strategic Partners: Standard Test Methods for the Nonwoven Industry

Glatfelter Sontara Asturias S.A.U

Technical Data Sheet to be revised annually. Results provided are measured with internal procedures inspired by the quoted norms if applicable. Minimum and maximum values are average and not individual results. These are not specifications and only to be used as indicative properties. All properties are typical values according to our current knowledge at the time of the last update of this publication. They are given for general guidance only – Glatfelter does not warrant any results and assumes no obligation or liability whatsoever in connection with this information. Please conduct your own tests to ensure consistency for your applications. The publication of these properties does not grant any right or license to any intellectual property of Glatfelter. MD = machine direction, CD = cross direction – Data last updated May 1, 2022
©2022 A Glatfelter Company. All rights reserved.

GLATFELTER