Sontara




## Empfohlene Reinraumklassen

**ISO** 8 | 9

**GMP** D

# Tuch Sontara EC White

pure[11]-Nr.: 1120944, Marke: Sontara

## Eigenschaften

- Marke: Sontara
- Flächengewicht in g/m²: 73 g/m²
- Struktur: Gewebe
- Material: Krepp
- Länge in cm: 30,5 cm
- Breite in cm: 42 cm
- Lieferform in Verpackung: gefaltet
- Verpackungsform: Spenderbox
- Anzahl in kleinster Unterverpackung: 250
- Gebrauch: Einweg
- Krepp: 100 %
- Flächengewicht in g/m²: 73 g/m²

we care

**pure[11] GmbH** |
Bavariafilmplatz 7 | D-82031 Grünwald
T +49 89 5589434 0
F +49 89 5589434 77
www.pure11.de
info@pure11.de

## Material

- Krepp

## Verpackung

- 250STK

## Produktvarianten

**pure[11]-Nr.: 1120944, Tuch Sontara EC White**

Größe: 31 x 42 cm (12 x 17"); Farbe: Weiß / VE: 250STK

**pure[11] GmbH** |
Bavariafilmplatz 7 | D-82031 Grünwald
T +49 89 5589434 0
F +49 89 5589434 77
www.pure11.de
info@pure11.de

Sontara®
A Magnera Brand

# Technical Data Sheet

Style K949SE
50.4% Woodpulp – 49.6% PET
Creped Smooth Embossed
White

## TYPICAL MATERIAL PROPERTIES

| TEST | ORIENTATION | UNITS | TARGETS | METHODS |
|---|---|---|---|---|
| Basis Weight | | $g/m^2$ | 73 | WSP 130.1 |
| Thickness | | mm | 0.53 | WSP 120.6 |
| Absorption Capacity | | % | 585 | WSP 10.1 |
| Extrinsic absorption capacity | | $ml/m^2$ | 422 | WSP 10.2 |
| Grab Tensile Strength | MD | N/4in | 142 | ASTM D5034 |
| | CD | N/4in | 73 | ASTM D5034 |
| Strip Tensile Strength | MD | N/5cm | 135 | WSP 110.4 |
| | CD | N/5cm | 55 | WSP 110.4 |

WSP = Worldwide Strategic Partners: Standard Test Methods for the Nonwoven Industry

Glatfelter Sontara Asturias S.A.U

Technical Data Sheet to be revised annually. Results provided are measured with internal procedures inspired by the quoted norms if applicable. Minimum and maximum values are average and not individual results. These are not specifications and only to be used as indicative properties. All properties are typical values according to our current knowledge at the time of the last update of this publication. They are given for general guidance only . MD = machine direction, CD = cross direction.
Magnera does not warrant any results and assumes no obligation or liability whatsoever in connection with this information. Please conduct your own tests to ensure consistency for your applications.
The publication of these properties does not grant any right or license to any intellectual property of Magnera.
Data last updated Jun 11, 2024
©2024 A Magnera Corporation. All rights reserved.