

Empfohlene Reinraumklassen

ISO 4 | 5 | 6 | 7 | 8 | 9

GMP C | D

Nitril-Handschuhe CELOS Glove 1.10

pure[11]-Nr.: 1105050, Marke: CELOS

Eigenschaften

- Antistatisch
- AQL (Acceptable Quality Level)-Wert: 1,5
- Chemikalienbeständig gegen Aceton: Level 0 (<10min)
- Chemikalienbeständig gegen Isopropanol (70%): Level 1 (10-30min)
- Chemikalienbeständigkeit - Typ: Typ B
- Handschuhtyp: Dünnfilm
- Im Reinraum hergestellt
- Länge in cm: 30 cm
- Länge in Inches: 11,8 ln
- Latexfrei
- Lebensmittelkonformität
- Material: Nitril
- Materialzusammensetzung: Reinmaterial
- Oberflächenbeschaffenheit: griffig
- Puderfrei
- Reißfestigkeit EN 455-2 ASTM in MPa: 20-30
- Rollrand
- Schutz vor Blut und Körpersekreten ISO 16604:2004
- Silikonfrei

pure[11] GmbH |
Bavariafilmplatz 7 | D-82031 Grünwald
T +49 89 5589434 0
F +49 89 5589434 77
www.pure11.de
info@pure11.de

we care

- Texturierte Fingerspitzen
- Passform Hand: beidhändig
- Verpackungsform: Beutel
- Viren-/Mikroorganismenschutz EN ISO 374-5:2016
- Vulkanisationsbeschleunigerfrei
- Wandstärke Mittelfinger in mm: 0,12 mm
- Marke: CELOS

Material

- Nitril

Verpackung

- 1000STK

pure¹¹ GmbH |
Bavariafilmplatz 7 | D-82031 Grünwald
T +49 89 5589434 0
F +49 89 5589434 77
www.pure11.de
info@pure11.de

Produktvarianten

pure[11]-Nr.: 1105050WHM, Nitril-Handschuhe CELOS Glove 1.10

Farbe: Weiß; Größe: M / VE: 1000STK

pure[11]-Nr.: 1105050WH3XL, Nitril-Handschuhe CELOS Glove 1.10

Farbe: Weiß; Größe: 3XL / VE: 1000STK

pure[11]-Nr.: 1105050WHL, Nitril-Handschuhe CELOS Glove 1.10

Farbe: Weiß; Größe: L / VE: 1000STK

pure[11]-Nr.: 1105050WHS, Nitril-Handschuhe CELOS Glove 1.10

Farbe: Weiß; Größe: S / VE: 1000STK

pure[11]-Nr.: 1105050WHXL, Nitril-Handschuhe CELOS Glove 1.10

Farbe: Weiß; Größe: XL / VE: 1000STK

pure[11]-Nr.: 1105050WHXS, Nitril-Handschuhe CELOS Glove 1.10

Farbe: Weiß; Größe: XS / VE: 1000STK

pure[11]-Nr.: 1105050WHXXL, Nitril-Handschuhe CELOS Glove 1.10

Farbe: Weiß; Größe: XXL / VE: 1000STK

TECHNICAL DATA SHEET

CELOS Nitrile Glove 1.10



CLEANROOM PRODUCTS | PERSONNEL

RECOMMENDED CLEANROOM CLASSES

ISO	3	4	5	6	7	8	9
GMP			A/B		C	D	

PRODUCT INFORMATION

MATERIAL	100 % pure Nitrile
PROCESS	Laundered with 0.2 micron filtered high resistivity DI water and packed in certified cleanroom environment
APPLICATION	Cleanroom glove with best in class fit and for highest cleanliness requirements
LENGTH	300 mm
CUFF THICKNESS	0.08 mm (+/-0.02 mm)
PALM THICKNESS	0.10 mm (+/-0.02 mm)
FINGERTIP THICKNESS	0.13 mm (+/-0.02 mm)
COLOR	Natural white
CHEM. PERFORMANCE	TYPE B, JKPT, VIRUS

TECHNICAL DATA SHEET

CELOS Nitrile Glove 1.10

CELOS®
a pure[11] brand

PRODUCTS

PART NUMBER	VARIANT	SIZE	STYLE	INNER PACKAGING	OUTER PACKAGING	QUANTITY PER CASE
1105050	**WH**XS	XS	Non-sterile	100 pcs/bag	10 bags/OB	1 OB/case
	WHS	S				
	WHM	M				
	WHL	L				
	WHXL	XL				
	WH2XL	2XL				
	WH3XL	3XL				

CHARACTERISTICS

- Personal Protective Equipment - Category III
- Glove of newest generation
- Ambidextrous
- Silicone and latex free
- Unique fit and textured fingertips
- Reduced allergy risk
- High tackiness for great grip
- Cleanroom produced and packed
- Without plasticizers, phthalates, silicone oil and amide
- No sulphur, accelerator and zinc added during compounding process
- Significantly lower levels of TiO_2
- Higher cleanliness levels achieved through the omission of color additives

PERFORMANCE PARAMETER

		SPECIFICATION	UNIT
Fluoride	F^-	< 0.010	µg/cm²
Chloride	Cl^-	< 0.300	µg/cm²
Nitrite	NO_2^-	< 0.050	µg/cm²
Bromide	Br^-	< 0.050	µg/cm²
Nitrate	NO_3^-	< 0.300	µg/cm²
Phosphate	PO_4^{3-}	< 0.050	µg/cm²
Sulphate	SO_4^{2-}	< 0.050	µg/cm²
Sodium	Na^+	< 0.050	µg/cm²
Calcium	Ca^{2+}	< 0.200	µg/cm²
Magnesium	Mg^{2+}	< 0.010	µg/cm²
Potassium	K^+	< 0.050	µg/cm²
Ammonium	NH_4^+	< 0.050	µg/cm²

PHYSICAL AND CHEMICAL PROPERTIES

	SPECIFICATION	UNIT
Tensile strength	≥ 18	MPa
Elongation	≥ 500	%
Particle count LPC (> 0.5 µm)	< 1,200	counts/cm^2
NVR (DI water)	< 3.00	µg/cm^2
Silicone oil, amide and DOP	Absent	-
Surface resistivity	< 10^{11}	ohm/sq
Static decay time	< 0.5	seconds
Tribo electric charge	< 20	volts

ADDITIONAL IMPORTANT PRODUCT INFORMATION

According to the EN 21420:2020 test, it is confirmed that during the production of CELOS gloves 1105050, none of the following chemicals are introduced into the production prosess, thus reducing allergic reactions.

- Thiruam disulfide
- Dithiocarbamates
- Mercaptobenzothiazole / MBT derivates
- 1.3 - diphenylguanidine
- Duphenylthiourea, dibuthylthiourea
- Formaldehyde
- Bisphenol A
- Bezoisothiazolinine
- Cethylpiridinium Chloride
- Triphenyl phophite, triphenyl phosphate, tricresyl phosphate
- Abietic acid derivates
- Nickel

PERFORMANCE PARAMETER

PARAMETER	TEST METHOD	RESULT
pH value	DIN EN 420:2010	Measured pH value: 6.4
Dangerous chemicals and micro-organisms	DIN EN 374-1 + A1:2018 DIN EN 374-5:2016	Pass
Air-Leak-Test	DIN EN 374-2:2015	Pass
Water-Leak-Test	DIN EN 374-2:2015	Pass
Permeation	DIN EN 16523-1:2015	See table below
Degradation	DIN EN 374-4:2014	See table below

1. Permeation

TEST CHEMICALS	CODE	SAMPLE 1	SAMPLE 2	SAMPLE 3
		Breakthrough [min]	Breakthrough [min]	Breakthrough [min]
N-heptane	J	40	34	39
Hydrogen peroxide (30 %)	P	> 480	> 480	> 480
Formaldehyde (37 %)	T	89	58	36
Sodium hydroxide (40 %)	K	> 480	> 480	> 480
Ethanol (70 %)	-/-	17	14	16
2-Propanol (70 %)	-/-	34	45	33
Hydrochloric acid (30 %)	-/-	> 480	> 480	> 480
Sulfuric acid (50 %)	-/-	> 480	> 480	> 480

2. Degradation

TEST CHEMICALS	CODE	DEGRADATION	STANDARD DEVIATION
		[%]	[%]
N-heptane	J	- 40.7	62.9
Hydrogen peroxide	P	31.6	6.5
Formaldehyde	T	18.8	36.4
Sodium hydroxide	K	-24.3	32.4

FOOD SUITABILITY

This data sheet shall give an overview of results for food contact testing of Cleanroom Nitrile CELOS® Glove 1.10. The results below reflect migration testing in accordance to the test specification § 31 LFGB (German Food and Feed Code). The product complies with the total migration limit as described. According to the kind and extent of tests performed the test item meets the requirements of the test specification LFGB § 31 and is therefore suitable for contact with foodstuff.

PARAMETER	TEST METHOD -STANDARD	RESULT
Sensory analysis	DIN 10955:2004	Pass
Smell transfer		Pass
Transfer of taste		Pass
Overall migration	DIN EN 1186 ff.:2002	See table below
Overall migration, Tenax	DIN EN 1186-13:2002	See table below
Acrylonitrile, migration	DIN EN 13130-3:2004	See table below
1,3-Butadiene, migration	DIN CEN / TS 13130-15:2005	See table below
Formaldehyde, content	DIN CEN / TS 13130-23:2005	See table below
Primary aromatic amines, migration	In-house method – quantification by HPLC-MS/MS	Pass
Metals, Natural or Synthetic Rubber	MS-0022823:2020	Pass
N-nitrosamines and N-nitrosatable substances	DIN EN 12868:2017	Pass
Polycyclic aromatic hydrocarbons (PAH)	AfPS GS 2014:01 PAK:2014	Pass

Sensory analysis

	CONTACT MEDIUM	PASS / FAIL
Smell transfer	Water	Pass
Transfer of taste	Water	Pass

The samples comply with the requirements of § 31 Para. 1 LFGB or Article 3 of Regulation (EC) 1935/2004.

Overall migration into Food Simulants

	OVERALL MIGRATION	PASS / FAIL
	[mg / dm²]	
Acetic Acid 3 %	4	Pass
Ethanol 50 %	7	Pass
Tenax	< 2	Pass

The samples comply with the limit value for products in contact with food according to the Consumer Goods Ordinance respectively Regulation (EU) No. 10 / 2011 and any amendments thereto.

Migration of Acrylonitrile and 1,3 – Butadiene

	ACRYLONITRILE		1,3 – BUTADIENE	
Migration Solution	Oil	Acetic Acid 3 %	Oil	Acetic Acid 3 %
Results (mg / kg)	< 0.005	< 0.005	< 0.01	< 0.01
Pass / Fail	Pass	Pass	Pass	Pass

The samples comply with the limit value for products in contact with food according to the Consumer Goods Ordinance respectively Regulation (EU) No. 10/2011 and any amendments thereto.

Formaldehyde content

	RESULT	PASS / FAIL
	[mg / l]	
Formaldehyde	< 1	Pass

The samples comply with the requirements according to the recommendation of the BfR part XXI „Commodities based on Natural and Synthetic Rubber".

Primary aromatic amines, migration

	RESULT	MIGRATION SOLUTION	PASS / FAIL
	[mg/kg] food simulant		
2,5-Dichloraniline	< 0.01	Acetic Acid 3 %	Pass
2,4,5-Trichloraniline	< 0.01	Acetic Acid 3 %	Pass
4-Chlor-3-methoxyaniline	< 0.01	Acetic Acid 3 %	Pass

Metals / Natural or Synthetic Rubber

	CATEGORY	RESULT	PASS / FAIL	REQUIREMENT
		[%]		[C = Category]
Lead	3	< 0.001	Pass	Lead impurities: **C 1**/**2**/**3*** commodities max. 0.003 % **Special C*** commodities max. 0.001 %
Zinc	3	< 1	Pass	Zinc content: **C 1**/**2**/**3*** commodities max. 3.0 % **Special C*** commodities max. 1.0 %

***C 1** [Category 1]
– Materials intended to be put in mouth or materials for toys intended to come into contact and with prolonged contact with the skin (longer than 30 s).

***C 2** [Category 2]
– Materials not covered by category 1 with foreseeable contact to skin for longer than 30 seconds (longer term skin contact) or repeated short term skin contact.

***C 3** [Category 3]
– Materials not covered by category 1 or 2 with foreseeable contact to skin up to 30 seconds (short term skin contact).

The samples comply with the requirement according to BfR recommendation XXI „Consumer goods based on natural and synthetic rubber".

pure11 GmbH | Sitz: Grünwald
Bavariafilmplatz 7 | D-82031 Grünwald
+49 89 5589434 0
+49 89 5589434 77
www.pure11.de
info@pure11.de

pure11 has made every effort to ensure the accuracy of information in this datasheet through continuous monitoring and testing. However, the information is provided "as is" without warranty of any kind. pure11 accepts no liability for the completeness, accuracy, or suitability of this information for specific applications. All information is based on current knowledge and experience, and users are asked to conduct their own tests to determine product suitability.