

pure[11]-Nr.: 1130060, Marke:

Eigenschaften

Empfohlene Reinraumklassen

ISO

GMP

we care

pure[11] GmbH |
Bavariafilmplatz 7 | D-82031 Grünwald
T +49 89 5589434 0
F +49 89 5589434 77
www.pure11.de
info@pure11.de

Material

-

Verpackung

- Box

Produktvarianten

pure¹¹-Nr.: 1130060,

pure¹¹-Nr.: 1130060BKYL2I, Reinraum-Klebeband "Safety" Antistatisch #2265-2

Farbe: Schwarz/Gelb; Breite: 2" / VE: 3STK

pure¹¹-Nr.: 1130060YL2I, Reinraum-Klebeband "Safety" Antistatisch #2265-2

Farbe: Gelb; Breite: 2" / VE: 3STK

UltraTape
Adhesive Tape & Labels for Critical Environments

PRODUCT DATASHEET

UT2265 Anti-static Cleanroom Printed Over Laminated Vinyl Marking Tape

DESCRIPTION

UltraTape 2265/ 0265 is a Cleanroom Anti-static tape available in multiple colors for floor, tool and safety marking, as well as a wide range of applications where opaque colors are needed. Printed and over laminated for extra durability and solvent resistance.

- Anti-static both sides of the tape
- Bright opaque colors and black printed ESD logo
- Solvent resistant
- Excellent durability and abrasion resistance

PROPERTIES

Backing	Vinyl base / PET over lamination / ESD Coated
Adhesive	Acrylic / ESD Coated
Backing Thickness	5.5 mils (0.140 mm)
Adhesive Thickness	1 mil (0.025 mm)
Adhesion to Stainless	28.8 oz/in (800g/25mm)
Surface Resistance – Backing Side	≤ 10E9
Surface Resistance – Adhesive Side	≤ 10E10
Peeling Static Voltage	< 100 V
Elongation	80%
Colors	Blue (BL), Black (BK), Black/Yellow (BY), Black/White (BW), Green (GR), Red (RE), Red/White (RW), White (WH), Yellow (YE), Orange (OR)

To achieve ultimate adhesion, the bonding surface should be clean, dry, and free of dirt and oils. The strength of the adhesive bond is dependent on the amount of surface area directly in contact with the adhesive. Firm pressure is recommended to achieve good adhesive to surface contact.

UltraTape recommends that each user conduct their own test to determine the product's suitability for the intended application and shall assume all risks and liabilities in connection therewith. Materials should be stored at 70°F (21C°) with 50% relative humidity.

9770 SW Wilsonville Road, Suite 400
Wilsonville, OR 97070
www.cleanroomtape.com

503.427.2880
503.482.5616

© UltraTape 2022 | Rev. 05/2022

ISO 9001:2015

UL LISTED

A division of DELPHON