


pure[11]-Nr.: 1107012, Marke:

Eigenschaften

Empfohlene Reinraumklassen

ISO

GMP

we care

pure[11] GmbH |
Bavariafilmplatz 7 | D-82031 Grünwald
T +49 89 5589434 0
F +49 89 5589434 77
www.pure11.de
info@pure11.de

Material

-

Verpackung

- Box

Produktvarianten

pure[11]-Nr.: 1107012,

pure[11]-Nr.: 1107012BLDINA4, Reinraumpapier #LCIB2025C

Farbe: Blau; Größe: DIN A4 / VE: 2500STK

pure[11]-Nr.: 1107012GNDINA4, Reinraumpapier #LCIG2017C

Farbe: Grün; Größe: DIN A4 / VE: 2500STK

pure[11]-Nr.: 1107012PKDINA4, Reinraumpapier #LCIK2029C

Farbe: Rosa; Größe: DIN A4 / VE: 2500STK

pure[11]-Nr.: 1107012WHDINA4, Reinraumpapier #LCIW2014C

Farbe: Weiß; Größe: DIN A4 / VE: 2500STK

pure[11]-Nr.: 1107012YLDINA4, Reinraumpapier #LCIY2016C

Farbe: Gelb; Größe: DIN A4 / VE: 2500STK

PURUS

Critical *Print*

For writing in critical enviroments

Cleanroom Paper

Critical Print paper is the most advanced line of clean paper and documentation available for the most demanding applications. Pureimage paper utilizes a Dual Binding Technology that is low in particles and created for low particle shed. Ideal for laser or ink jet printers, photocopying and hand writing in a controlled environment. Pureimage paper is also bonded without organic fillers and yet completely recyclable.

Sizes A2, A3, A4, A5, A6 Paper and Notebooks

Colours White, Blue, Green, Yellow and Pink.

Packaging

Paper Size	Total Sheets	Packs per Case	Sheets per Ream
A2	1000	4	250
A3	1250	5	250
A4	2500	10	250
A5	5000	20	250
A6	10000	40	250

Notebook Size	Total Sheets	Packs per Case	Sheets
A4	2500	10	100
A5	5000	20	100
A6	10000	40	100

Technical Specifications

	80 gsm / 22lb	105 gsm / 28 lb
Basis Weight (g/m2)	70-90	95 – 115
Caliper (micron)	94 – 104	110 – 120
Tear Strength MD/CD	74/75	80/81
Brightness (%)	88 – 92	88 – 92

Tensile Strength Machine Direction: 5.0 kg/15mm*
Cross Direction: 2.5 kg/15mm*

Partical size >.5µm
(170 pt/cm2 via Liquid Particle Counter)

Anion

Chloride (Cl)	0.420 µg/cm²
Nitrite (NO^2)	<0.0015 µg/cm²
Bromide (Br)	<0.0015 µg/cm²
Phosphate (PO^4)	<0.0038 µg/cm²
Sulfate (SO^4)	0.100 µg/cm²

Cation

Lithium (Li)	<0.0015 µg/cm²
Sodium (Na)	2.020 µg/cm²
Ammonium (NH^4)	0.020 µg/cm²
Potassium (K)	0.100 µg/cm²



*Tensile strength determined by the Elmendorf tear test.

Purus Cleanroom Solutions Ltd | B4 Corcanree Business Park, Dock Road, Limerick, Ireland, V94 X070
(+353) 61 496662 | sales@puruseurope.com | puruseurope.com