



Nitril-Handschuhe TouchNTuff 92-665

pure¹¹-Nr.: 05332, Hersteller: Ansell

Zusammenfassung

- Neue pure11-Artikelnummer (ab 01.07.2023): 1105332
- Material: Nitril
- Beidhändig tragbar
- Puderfrei
- Latexfrei
- AQL-Wert (Acceptable Quality Level): 1.5
- Texturierte Fingerspitzen
- Einfache Wandstärke 0,10 mm (Mittelfinger)

Empfohlene Reinraumklassen

ISO

3

4

5

6

7

8

9

GMP

D

Produktvarianten

pure¹¹-Nr.: 05332B6c

Farbe: Blau / Größe: 6,5-7,0 / Herst.-Nr.: 92-665 / VE: 1.000 Stück

pure¹¹-Nr.: 05332B7c

Farbe: Blau / Größe: 7,5-8,0 / Herst.-Nr.: 92-665 / VE: 1.000 Stück

pure¹¹-Nr.: 05332B8c

Farbe: Blau / Größe: 8,5-9,0 / Herst.-Nr.: 92-665 / VE: 1.000 Stück

pure¹¹-Nr.: 05332B9c

Farbe: Blau / Größe: 9,5-10,0 / Herst.-Nr.: 92-665 / VE: 1.000 Stück

Quelle: <https://www.pure11.de/nitril-handschuhe-touchntuff-92-665>



Nitrile



Lab & Utility

TouchNTuff®

92-665 92-670 Nitrile Glove

Textured Single Use Nitrile Gloves

FEATURES AND BENEFITS:

Excellent Puncture Resistance

Three times the puncture resistance of latex or PVC disposables.

Comfort and Chemical Resistant

Made from an innovative nitrile compound which offers outstanding chemical and mechanical properties, comfort and dexterity

100% Nitrile

Contains no waxes, silicone or plasticizers.

Avoid Cuff Roll Down

Rolled cuff. Provides added protection at wrist and ensures a secure fit.

Improved Grip

Textured finish on fingertips.
Improved grip.



TECHNICAL DATA SHEET:

PRODUCT INFORMATION:

	92-665	92-670
Material	Nitrile	
Color	Light Blue	
Glove Design	Ambidextrous, Powder Free, Textured Fingers, Long Cuff	Ambidextrous, Powder Free, Textured Fingers
Cuff	Beaded Cuff	
Audit Standards	ISO 9001	
Quality Control	EN420, EN374/1,2,3, ASTM D 6319, FDA 21 CFR 177-2600, Arrete 09/11/04, European Regulation 1935/2004, German Recommendation for Food Commodities.	
Packaging	100 gloves per dispensers, 10 dispensers per shipper carton, 1000 gloves per shipper cartons	
Storage	Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition.	
Country of Origin	Thailand	

PHYSICAL PROPERTIES:

PROPERTY		TYPICAL VALUES				TESTING METHOD
	SIZE	S 6½-7	M 7½-8	L 8½-9	XL 9½-10	ASTM D3767/EN 420
Length (mm)	92-665	300	300	300	300	
	92-670	240	240	240	240	
Average Palm Width (mm)		85	96	105	111	

Freedom from Holes (Inspection level I)	1.5 AQL	ASTM D5151/EN 374-2
Palm Thickness Single Wall	(mm: 0.11) / (mils: 4.3)	ASTM D3767/EN 420

	BEFORE AGING	AFTER AGING	
Ultimate Tensile Strength	> 14 Mpa	> 14 Mpa	ASTM D 412-06a
Elongation at Break (%)	> 500	> 400	ASTM D 412-06a
Force at break (N)	> 6	> 6	EN 455-2

ORDERING INFORMATION:

	SIZE	S 6½-7	M 7½-8	L 8½-9	XL 9½-10
92-665	ASPN	588782	588783	588784	588785
92-670	ASPN	588170	588171	588172	588173



CE 0493

For additional information visit us at www.ansell.com, or call us at

North America, Latin America and Caribbean: +1800 800 0444

Asia Pacific: +852 2185 0600

Europe: +32 2 528 74 00

Australia: +61 3 9270 7270

® and ™ are trademarks owned by Ansell Limited or one of its affiliates. © 2013 All Rights Reserved.

Ansell