



Tuch Essentra C8

pure¹¹-Nr.: 06043, Hersteller: ESSENTRA

Zusammenfassung

- Neue pure¹¹-Artikelnummer (ab 01.07.2023): 1106043
- Material: Polyester/Zellulose
- Gewicht: 68 g/m²
- Vliesstoff aus Zellulose und Polyester
- Hydroverfestigt (nonwoven)
- Reinraumbuch mit spezieller "Twill"-Oberfläche
- Strukturierte Oberfläche zur Beseitigung von Verunreinigungen
- Lieferform: gelegt

Empfohlene Reinraumklassen

ISO

3

4

5

6

7

8

9

GMP



Produktvarianten

pure¹¹-Nr.: 060432323

Farbe: Weiß / Maße: 23 x 23 cm (9 x 9") / Herst.-Nr.: C8 / VE: 300 Stück

pure¹¹-Nr.: 060433131

Farbe: Weiß / Maße: 31 x 31 cm (12 x 12") / Herst.-Nr.: C8 / VE: 150 Stück

Quelle: <https://www.pure11.de/tuch-essentra-c8>

pure¹¹ GmbH

Bavariafilmplatz 7 | D-82031 Grünwald

Geschäftsführer: Gitte Hansen, Julian Kropp

AG München HRB 171307

T +49 89 5589434 0

F +49 89 5589434 77

www.pure11.de

info@pure11.de



ESSENTRA

POROUS TECHNOLOGIES

C8

Hydroentangled blend of polyester and cellulose embossed with a "Twill Like" surface pattern, hills for wiping and valleys to trap removed contaminants.

Property	Typical Value	Test Method
Basis Weight		
(oz/yd ²)	2.0	
(g/m ²)	68	
Thickness		
(mils)	14	
(mm)	0.356	
Sorbency Capacity		
Intrinsic (mL/g)	4.2	IEST-RP-CC004.3
Extrinsic (mL/m ²)	296	IEST-RP-CC004.3
Nonvolatile Residue (NVR) (mg/g)		
Deionized Water	0.013	IEST-RP-CC004.3
Isopropyl Alcohol	0.02	IEST-RP-CC004.3
Ions (ppm)		
Sodium	<2	IEST-RP-CC004.3
Chloride	25	IEST-RP-CC004.3
Particles (million/m²)		
> 0.5 µm	194	IEST-RP-CC004.3

Notes:

- 1) Data shown are typical values and should not be used as product specifications.
- 2) Valid product comparisons may only be obtained through side-by-side testing in the same test facility, under similar conditions. Current and/or comparison data may be available. Please contact an Essentra representative for details.
- 3) Essentra Porous Technologies makes general recommendations on which wipers are suitable for different cleanroom classifications. However, specific applications may affect that recommendation. The final decision should be made by the end user for their particular application.

Effective: 05/07

ESSENTRA POROUS TECHNOLOGIES

2255 Westover Road
Chicopee, MA 01022

T (800) 628-8606
F (413) 592-4112
www.essentraporoustechnologies.com